

The information contained in this drawing is the sole property of Coil Winding Specialist Inc (CWS). Any reproduction in part or whole without written permission of CWS is prohibited.

## T25-1

### Features

Highest carbonyl permeability.  
Applies to high Q below 1 MHz, for utilization of band transformer range within 50-500 MHz

Electrical Specifications				
Item	Unit/Symbol	Condition	Value	Tol.
A <sub>L</sub>	nH/N <sup>2</sup>	Typ.	7	± 10%
L <sub>e</sub>	cm	N/A	1.50	Typ.
A <sub>e</sub>	cm <sup>2</sup>	N/A	0.037	Typ.
V <sub>e</sub>	cm <sup>3</sup>	N/A	0.055	Typ.
Approx. Material Density	g/cm <sup>3</sup>	N/A	6.4	Typ.
Permeability	μ <sub>0</sub>	N/A	20	± 10%
Temperature Stability	+ppm/°C	N/A	280	Typ.

Resonant Circuit (---) and Broadband Frequency Range (+++)											
Mix	Range (MHz)	2-50 KHz	50-250 KHz	250-500 KHz	500KHz-2MHz	2-10 MHz	10-40 MHz	40-150 MHz	150-250 MHz	250-500 MHz	500 MHz to 1GHz
42	0.3-80	-----									
3	0.02-1	-----									
8	0.02-1	-----				+++++					
1	0.15-3		-----						+++++		
15	0.15-3		-----								
2	0.25-10		-----								
7	1-25		-----								
4	3-40		-----								
6	3-40		-----						+++++		
10	15-100		-----							+++++	
17	20-200		-----								
12	30-250		-----								
0	50-350		-----								+++++

REVISION HISTORY					
REV	ECN	DESCRIPTION	SIGN & DATE		
			BY	DATE	AP. DATE
A		Production release	EO	3/7/13	JL 3/7/13



Case Dimensional Tolerances				
	in	tol.	mm	tol.
B (Outer Diameter)	0.255	0.015	6.48	0.38
A (Inner Diameter)	0.120	0.015	3.05	0.38
H (Height)	0.096	0.020	2.44	0.51
Weight 0.35 g				

**For additional detail, specifications and charts see:**

[http://www.bytemark.com/products/IPCores\\_index.html](http://www.bytemark.com/products/IPCores_index.html)

$$\text{Temperature Rise : } \Delta T(^{\circ}\text{C}) = \left[ \frac{\text{Total Power Dissipation (milliwatts)}}{\text{Surface Area (cm}^2\text{)}} \right]^{0.833}$$

$$\text{Required turns} = \left[ \frac{\text{desired L (nH)}}{A_L \left( \frac{\text{nH}}{\text{N}^2} \right)} \right]^{\frac{1}{2}}$$

$$\text{Peak AC Flux Density: } B_{pk} = \frac{E_{avg} 10^8}{4ANf}$$

$$\text{Magnetizing Force: } H = \frac{0.4\pi N I}{\ell}$$

L = inductance  
nH = nanohenries  
H = oersteds (Oe)  
N = Number of turns  
I = Current (amperes)  
ℓ = Mean Magnetic Path (cm)  
A = Cross-sectional area (cm<sup>2</sup>)  
f = frequency (hertz)  
B<sub>pk</sub> = Gauss (G)

UNLESS OTHERWISE SPECIFIED  
DIMENSIONING AND TOLERANCE PER ANSI Y14.5M  
ALL DIMENSIONS ARE IN INCHES AND [MILLIMETERS].  
TOLERANCE INCHES:  
.XXX=±.005 .XX=±.015 <math>\angle=±0^{\circ}30'</math>  
TOLERANCE METRICS:  
.XXX=±.127 .XX=±.38 <math>\angle=±0^{\circ}30'</math>  
ANGLE PROJECTION   
DO NOT SCALE DRAWING

CODE IDENT	MFG. P/N	DESCRIPTION	ITEM NO.
PARTS LIST			
AUTOCAD	X	www.coilws.com www.cwsbytemark.com	CWSBYTEMARK 353 West Grove Ave. Orange, CA. 92865
SOLIDWORKS			
DRAWN	EO 3/7/13	TITLE: Iron Powder Core: Material Mix 1 (Carbonyl C), Blue/Clear	
CHECKED	JL 3/7/13		
ENGR.	JL 3/7/13		
APPR.	JL 3/7/13		
SIZE DWG. NO.		T25-1	REV A
SCALE		N/A	SHEET 1 OF 1